



金源化工私人有限公司
NOBLE SPECIALTY SDN. BHD. (182260-U)

J.B. - No. 6, Jalan Masai Lama, Bandar Seri Alam, 81750 Masai, Johor.
Tel: 07-3881930/31 Fax: 07-3881932 E-mail: enquiries@noblespecialty.com
K.L. - No. 96, Jalan Taming 6, Kawasan Perusahaan Taman Taming Jaya,
43300 Seri Kembangan, Selangor. Tel: 03-89621818 Fax: 03-89621931
P.P. - No. 11, Lorong Teguh 3, Taman Industri Teguh, Permatang Tinggi,
14000 Bukit Mertajam, Pulau Pinang. Tel: 04-5682231/2232 Fax: 04-5682213



SPECIFICATION

COMMODITY : **MODIFIED STARCH
MT-01B**

ORIGIN : **Thailand**

PACKING : **25kgs Bag**



CHARACTERISTICS		SPECIFICATION	METHOD
Appearance		White or off-white powder	Visual checking
Moisture	% Max	14	Drying at 105°C for 4hrs
Whiteness	% Min	90	Whiteness meter
Ash	% Max	0.5	Residue after heating at 575°C for 4hrs
pH	- Range	4.5 - 6.5	10% Slurry
So2	ppm Less than	10	Rankine method
Total Plate Count	CFU/g Max.	10000	AOAC 966.23
Yeast	CFU/g Max.	100	Agar Plate Incubations (PDA 10%)
Mould	CFU/g Max.	100	Agar Plate Incubations (PDA 10%)
E.coli	/g -	Negative	BGLB Method Etc.
Viscosity at 95°C,0	BU Min.	400	Bratender viscosograph, 6%